

G-2115-2

Calcium Sulfonate Complex Grease

G-2115-2 Grease is a member of a family of technologically advanced greases which have been developed by complexing modified overbased calcium sulfonates. This technology, developed and patented by Chemtura, is characterized by exceptional mechanical stability, high dropping point, high load carrying performance, reduced wear, and excellent resistance to water and corrosion. This technology equals and in many ways outperforms other premium, high temperature greases such as Lithium Complex, Aluminum Complex and Polyurea.

FEATURES AND BENEFITS

Thermal and Mechanical Stability

- Superior mechanical stability versus other thickeners, particularly in the presence of heat and water
- High dropping point, typically in excess of 300°C

Load Carrying & Wear Protection

- Excellent EP and AW properties inherent in the thickener
- Does not require the use of additional additives

Low Temperature Properties

- Excellent mobility and torque at temperatures down to -40°C

Corrosion Resistance

- Sulfonates are known and used for their excellent rust prevention properties
- This property is inherent in the thickener
- Will easily outperform all other technologies

Resistance to Water

- Excellent resistance to water washout

Resistance to Oxidation

- The use of a premium antioxidant and a high performance, low viscosity PAO ensures superior thermal and oxidation stability
- Bearing life typically in excess of 200 hours

APPLICATION AREAS

G-2115-2 Grease is a low viscosity synthetic formulation which offers superior performance over a wide operating temperature range. It can be used in high speed bearings, sealed for life bearings, and in most extended life operations.

It easily exceeds the requirements for NLGI GC/LB certification.



TYPICAL DATA

PROPERTIES	TEST METHOD	G-2115-2
NLGI Grade	ASTM D217	2
Colour	Visual	Tan
Texture	Visual	Smooth
Dropping Point, °F	ASTM D2265	605
Consistency, 60 strokes	ASTM D217	280
Base Oil Viscosity, cSt @ 40°C	ASTM D445	50
Mechanical Stability Worked 100,000 strokes, % change	ASTM D217	2.4
Worked 10,000 strokes, with 50/50 water, %		8.0
Timken OK Load, kg	ASTM D2509	27.2
4-Ball EP: LWI, kgf	ASTM D2596	62
Weld Point, kg		500
4-Ball Wear, mm	ASTM D2266	0.42
Rust Test, rating	ASTM B1743	Pass
Salt Fog Corrosion, 1 mil d.f.t., hours	ASTM B177	>1000
Copper Corrosion, rating	ASTM D4048	1B
Wheel Bearing Leakage, grams	ASTM D4290	4.0
Bearing Life Performance, hours	ASTM D3527	220
Bomb Oxidation, psi drop after 1000 hours	ASTM D942	6.0
Oil Separation, % loss	ASTM D1742	0.2
Water Washout at 80°C, % removed	ASTM D1264	0.5
Low Temperature Torque, @-40 C, Nm	ASTM D4693	2.5
Mobility @ -35oC, g/minute	US Steel Method	9.0

The values quoted above are typical of normal production. They do not constitute a specification.

May be available in other NLGI Grades, to a minimum cone penetration of 260 mm/10 (Grade 2.5).
 (Performance data may vary between grades).

HANDLING INFORMATION

G-2115-2 Grease may be handled using conventional grease handling and dispensing methods.

SAFETY INFORMATION

For more extensive information on the safe handling and use of this product, see the Material Safety Data Sheet.

SHIPPING INFORMATION

Petroleum Lubricating Grease available in a wide range of containers.



A company of the
LANXESS
Group

The information contained herein relates to a specific Chemtura product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. NOTHING IN THIS TECHNICAL DATA SHEET SHALL BE CONSTRUED TO CONSTITUTE A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, REGARDING THE PRODUCTS CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner.

The Chemtura logo is a trademark of Chemtura Corporation or one of its subsidiaries.

Copyright © 2016 Chemtura Corporation. All rights reserved.

North America

+1.800.325.6252
customer.care@chemtura.com

Europe, Middle East & Africa

+44.161.875.3800
emea.export@chemtura.com

South & Central America

+55.19.3522.5000
Atendimento.cliente@chemtura.com

Asia Pacific

+86.21.3866.6509
orders.apac@chemtura.com

